

Primary Fiber Coating KG190-4

Product Properties

LED curing , low modulus, good elongation

Characteristics

Liquid Coating

Typical Value

Viscosity (25°C)	5400cps
Refractive Index (23°C)	1.473
Density (23°C)	1.05kg/l

Cured Film

Typical Value

By DMA	
Temperature when E'=1000Mpa	-55.4°C
Temperature when E'=100Mpa	-47.2°C
Modulus at 2.5% strain	1.06MPa
Elongation	100%
Tensile strength	0.50MPa
Curing speed (at 95% of relative curing degree)	0.25J/cm ²
Shrinkage upon curing	2.7%
Refractive Index (23°C)	1.477
Weight loss	
8 weeks at 85°C	-4.3%
8 weeks at 125°C	-5.7%
Adhesion to glass (23°C)	0.9N


Storage Conditions

KG coatings is available in 10kg or 1000kg plastic bottle which prevent exposure of the content to UV light. It is recommended that KG coatings be stored in a dry place in unopened, undamaged, original containers at temperatures between 0°C and 35°C. Storage or shipment in cold conditions may result in a phase separation which is reversible and is corrected by heating for 24 hours at 40°C .

Shelf Life


KG190-4 has a recommended shelf life of 12 months from the date of manufacture, provided that the above stated storage conditions are properly maintained.

Viscosity vs. Temperature



$$1 \text{ cps} = 1 \text{ mPa} \cdot \text{s}$$

Dynamic Properties vs Temperature



The data contained herein are based on Phichem lab test result and are believed to be reliable. Phichem recommends that the users take test to determine the suitability of a product in particular processing or application/use.